

Politer 30 GF V0A

Polybutylene Terephthalate

Poliblend S.p.a.

Message:

Politer 30 GF V0A is a Polybutylene Terephthalate (PBT) material filled with 30% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, or Latin America. Primary attribute of Politer 30 GF V0A: Flame Rated.

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Halogen		
Features	Self Extinguishing		
Appearance	Natural Color		
Physical	Nominal Value	Unit	Test Method
Density	1.72	g/cm ³	ISO 1183
Molding Shrinkage	0.40 to 0.80	%	
Water Absorption (23°C, 24 hr)	0.030	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10000	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Yield	125	MPa	
Break	125	MPa	
Tensile Strain			ISO 527-2
Yield	2.0	%	
Break	2.0	%	
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	7.0	kJ/m ²	ISO 180/A
Unnotched Izod Impact Strength	50	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	220	°C	ISO 75-2/B
1.8 MPa, Unannealed	205	°C	ISO 75-2/A
Continuous Use Temperature ¹	125	°C	
Vicat Softening Temperature	215	°C	ISO 306/A120
Ball Pressure Test (165°C)	Pass		IEC 60695-10-2
Melting Temperature	225	°C	DSC
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	V-0		

1.60 mm	V-0		
3.20 mm	V-0		
Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	120 to 130	°C	
Drying Time	> 3.0	hr	
Processing (Melt) Temp	240 to 260	°C	
Mold Temperature	70.0 to 90.0	°C	
NOTE			
1.	Without Load		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT