

Makrolon® FR7067

Polycarbonate

Covestro - Polycarbonates

Message:

MVR (300 °C/1.2 kg) 20 cm³/10 min; flame retardant; UL 94V-0/1.5 mm and 5VA/3.0 mm; medium viscosity; UV stabilized; easy release; injection molding
- melt temperature 260 - 300 °C; available in transparent and translucent colors; electrical/electronic

General Information			
UL YellowCard	E41613-100924380		
Additive	Flame Retardant		
	UV Stabilizer		
Features	Flame Retardant		
	Good Mold Release		
	Low Viscosity		
	Medium Viscosity		
Uses	Electrical/Electronic Applications		
RoHS Compliance	RoHS Compliant		
Appearance	Clear/Transparent		
	Colors Available		
	Translucent		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	20.0	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2600	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield, 23°C	75.0	MPa	
Break, 23°C	75.0	MPa	
Tensile Strain			ISO 527-2/50
Yield, 23°C	5.0	%	
Break, 23°C	100	%	
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
Notched Izod Impact Strength ¹			ISO 7391
-30°C, Complete Break	8.0	kJ/m ²	
23°C, Complete Break	8.0	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature			
0.45 MPa, Unannealed	105	°C	ISO 75-2/B
1.8 MPa, Unannealed	95.0	°C	ISO 75-2/A
Vicat Softening Temperature	110	°C	ISO 306/B120
RTI Elec (1.50 mm)	80.0	°C	UL 746
RTI Imp (1.50 mm)	80.0	°C	UL 746
RTI Str (1.50 mm)	80.0	°C	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.50 mm, CL,WT	V-0		
3.00 mm, CL,WT	V-0		
3.00 mm, CL, WT	5VA		
Glow Wire Flammability Index			IEC 60695-2-12
1.50 mm	960	°C	
3.00 mm	960	°C	
Glow Wire Ignition Temperature			IEC 60695-2-13
1.50 mm	960	°C	
3.00 mm	960	°C	
Optical	Nominal Value	Unit	Test Method
Transmittance (3000 μm)	88.0	%	ISO 13468-2
Haze (3000 μm)	2.0	%	ISO 14782
Additional Information	Nominal Value		
ISO Shortname	ISO 7391-PC,MFLR,(,)-18-9		
NOTE			

1. Based on ISO 180-A, 3 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

