

NORYL PPX™ PPX7200 resin

Polyphenylene Ether + PS + PP

SABIC Innovative Plastics

Message:

PP+PPE+PS. Improved chemical resistance and surface aesthetics in injection molded applications. NSF61-capable. UL-94 HB listed.

General Information			
Features	Good chemical resistance		
	Excellent appearance		
Agency Ratings	NSF 61		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	0.988	g/cm ³	ASTM D792
--	0.990	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	16	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (260°C/5.0 kg)	18.0	cm ³ /10min	ISO 1133
Molding Shrinkage			Internal method
Flow: 3.20mm	0.60 - 0.80	%	Internal method
Transverse flow: 3.20mm	0.60 - 0.80	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.050	%	ISO 62
Equilibrium, 23°C, 50% RH	0.020	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	1240	MPa	ASTM D638
--	1670	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	33.8	MPa	ASTM D638
Yield	34.0	MPa	ISO 527-2/50
Fracture ³	27.6	MPa	ASTM D638
Fracture	28.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	10	%	ASTM D638
Yield	8.2	%	ISO 527-2/50
Fracture ⁵	130	%	ASTM D638
Fracture	120	%	ISO 527-2/50

Flexural Modulus			
50.0mm span ⁶	1450	MPa	ASTM D790
-- ⁷	1610	MPa	ISO 178
Flexural Stress			
--	48.0	MPa	ISO 178
Yield, 50.0mm span ⁸	49.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹			ISO 179/1eA
-30°C	6.1	kJ/m ²	ISO 179/1eA
23°C	12	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength ¹⁰			ISO 179/1eU
-30°C	80	kJ/m ²	ISO 179/1eU
23°C	No Break		ISO 179/1eU
Notched Izod Impact			
-30°C	0.85	J/m	ASTM D256
23°C	150	J/m	ASTM D256
-30°C ¹¹	8.0	kJ/m ²	ISO 180/1A
23°C ¹²	14	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	1400	J/m	ASTM D4812
-30°C ¹³	No Break		ISO 180/1U
23°C ¹⁴	No Break		ISO 180/1U
Instrumented Dart Impact (23°C, Total Energy)	36.2	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	110	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	71.1	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹⁵	73.4	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	146	°C	ASTM D1525 ¹⁶
--	103	°C	ISO 306/B50
--	107	°C	ISO 306/B120
Linear thermal expansion coefficient			ASTM E831, ISO 11359-2
Flow: -40 to 40°C	9.9E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Lateral: -40 to 40°C	1.1E-4	cm/cm/°C	ASTM E831, ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	60.0 - 65.6	°C	
Drying Time	2.0 - 4.0	hr	
Drying Time, Maximum	8.0	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	30 - 70	%	

Rear Temperature	227 - 277	°C
Middle Temperature	238 - 282	°C
Front Temperature	249 - 288	°C
Nozzle Temperature	260 - 288	°C
Processing (Melt) Temp	260 - 288	°C
Mold Temperature	32.2 - 48.9	°C
Back Pressure	0.345 - 0.689	MPa
Screw Speed	20 - 100	rpm
Vent Depth	0.038 - 0.051	mm

NOTE

1.	50 mm/min
2.	Type 1, 50mm/min
3.	Type 1, 50mm/min
4.	Type 1, 50mm/min
5.	Type 1, 50mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*4 sp=62mm
10.	80*10*4 sp=62mm
11.	80*10*4
12.	80*10*4
13.	80*10*4
14.	80*10*4
15.	80*10*4 mm
16.	标准 B (120°C/h), 载荷2 (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

