

SITRALIN 21E / C6PS soul

Acrylonitrile Styrene Acrylate + Nylon

SITRAPLAS GmbH

Message:

Material: Polyamid with ASA

General Information			
Resin ID (ISO 1043)	>PA+ASA<		
Physical	Nominal Value	Unit	Test Method
Density	1.10	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (260°C/5.0 kg)	21.0	cm ³ /10min	ISO 1133
Molding Shrinkage ¹	0.20 to 0.60	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2200	MPa	ISO 527-2/1
Tensile Stress			
Yield	49.0	MPa	ISO 527-2/50
Break	40.0	MPa	ISO 527-2/5
Tensile Strain (Yield)	6.0	%	ISO 527-2/50
Nominal Tensile Strain at Break	30	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	25	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	135	°C	ISO 306/B50
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
NOTE			
1.	60 x 60 x 2 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT