

Rilsan® BMNO F15

Polyamide 11

Arkema

Message:

Rilsan® BMNO F15 is a Polyamide 11 (Nylon 11) product. It can be processed by injection molding and is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Characteristics include:

Eco-Friendly/Green

Medium Viscosity

Plasticized

General Information			
Features	Medium Viscosity		
	Plasticized		
	Renewable Resource Content		
Appearance	Natural Color		
Forms	Pellets		
	Powder		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792
Water Absorption			ASTM D570
24 hr	0.30	%	
Saturation	1.1	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	53		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	40.7	MPa	ASTM D638
Tensile Elongation (Break)	370	%	ASTM D638
Flexural Modulus	152	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-40°C	21	J/m	
23°C	No Break		
Thermal	Nominal Value	Unit	
Melting Temperature	184	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

