

Hostaform® M10AE

Acetal (POM) Copolymer

Celanese Corporation

Message:

POM copolymer

Stiff-flowing type with high melt strength; good chemical resistance to solvents, fuel and strong alkalis as well as good hydrolysis resistance; high resistance to thermal and oxidative degradation.

Monomers and additives are listed in EU-Regulation (EU) 10/2011

FDA compliant according to 21 CFR 177.2470

Burning rate ISO 3795 and FMVSS 302 < 100 mm/min for a thickness more than 1 mm.

Ranges of applications: For extrusion blow molding, and for injection molding thick-walled, void-free molded parts.

General Information			
Features	Solvent resistance		
	Good melt strength		
	Good chemical resistance		
	alkali resistance		
	Fuel resistance		
	Hydrolysis resistance		
Uses	Blow molding applications		
	Thick wall fittings (parts)		
Agency Ratings	FDA 21 CFR 177.2470		
	Europe 10/1/2011 12:00:00 AM		
RoHS Compliance	Contact manufacturer		
Processing Method	Blow molding		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	0.900	cm ³ /10min	ISO 1133
Water Absorption (Saturation, 23°C)	0.65	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2900	MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	65.0	MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	9.0	%	ISO 527-2/1A/50
Nominal Tensile Strain at Break	25	%	ISO 527-2/1A/50

Tensile Creep Modulus			ISO 899-1
1 hr	2400	MPa	ISO 899-1
1000 hr	1200	MPa	ISO 899-1
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	8.0	kJ/m ²	ISO 179/1eA
23°C	10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	200	kJ/m ²	ISO 179/1eU
23°C, local fracture	220	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	97.0	°C	ISO 75-2/A
Melting Temperature ¹	167	°C	ISO 11357-3
CLTE - Flow	1.3E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+14	ohms · cm	IEC 60093
Dielectric Strength	28	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	4.00		IEC 60250
1 MHz	4.00		IEC 60250
Dissipation Factor			IEC 60250
100 Hz	2.0E-3		IEC 60250
1 MHz	5.0E-3		IEC 60250
Comparative Tracking Index	600	V	IEC 60112
Injection	Nominal Value	Unit	
Drying Temperature	120 - 140	°C	
Drying Time	3.0 - 4.0	hr	
Suggested Max Moisture	0.15	%	
Hopper Temperature	20.0 - 30.0	°C	
Rear Temperature	170 - 180	°C	
Middle Temperature	180 - 190	°C	
Front Temperature	190 - 200	°C	
Nozzle Temperature	190 - 210	°C	
Processing (Melt) Temp	190 - 210	°C	
Mold Temperature	80.0 - 120	°C	
Injection Pressure	60.0 - 120	MPa	
Injection Rate	Slow-Moderate		
Holding Pressure	60.0 - 120	MPa	
Back Pressure	0.00 - 4.00	MPa	
Injection instructions			

Manifold Temperature: 190 to 210°C Zone 4 Temperature: 190 to 210°C Feed Temperature: 60 to 80°C

NOTE

1. 10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT