

LNP™ LUBRICOMP™ DL001 compound

Polycarbonate
SABIC Innovative Plastics

Message:

LNP LUBRICOMP DL001 is a compound based on Polycarbonate resin containing PTFE. Added features of this material include: Internally Lubricated.
Also known as: LNP* LUBRICOMP* Compound DL-4010
Product reorder name: DL001

General Information			
UL YellowCard	E207780-101343861		
Additive	PTFE lubricant		
Features	Lubrication		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow: 24 hours	0.70 - 0.90	%	ASTM D955
Transverse flow: 24 hours	0.90 - 1.1	%	ASTM D955
Vertical flow direction: 24 hours	0.96	%	ISO 294-4
Flow direction: 24 hours	0.78	%	ISO 294-4
Water Absorption (24 hr, 50% RH)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2070	MPa	ASTM D638
--	2190	MPa	ISO 527-2/1
Tensile Strength			
Yield	56.5	MPa	ASTM D638
Yield	54.0	MPa	ISO 527-2
Fracture	51.7	MPa	ASTM D638
Fracture	53.0	MPa	ISO 527-2
Tensile Elongation			
Yield	6.2	%	ASTM D638
Yield	6.1	%	ISO 527-2
Fracture	77	%	ASTM D638
Fracture	170	%	ISO 527-2
Flexural Modulus			
--	2070	MPa	ASTM D790
--	2100	MPa	ISO 178
Flexural Stress	70.0	MPa	ISO 178
Coefficient of Friction			ASTM D3702 Modified
With self-dynamics	0.39		ASTM D3702 Modified

With Self-Static	0.32		ASTM D3702 Modified
Wear Factor - Washer	91.5	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	160	J/m	ASTM D256
23°C ²	13	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	2400	J/m	ASTM D4812
23°C ³	180	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	39.6	J	ASTM D3763
--	49.4	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	142	°C	ASTM D648
0.45 MPa, unannealed, 64.0mm span ⁴	142	°C	ISO 75-2/Bf
1.8 MPa, unannealed, 3.20mm	132	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ⁵	129	°C	ISO 75-2/Af
Linear thermal expansion coefficient			ASTM E831, ISO 11359-2
Flow: -40 to 40°C	7.4E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Lateral: -40 to 40°C	7.6E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	293 - 304	°C	
Middle Temperature	304 - 316	°C	
Front Temperature	310 - 321	°C	
Processing (Melt) Temp	299 - 316	°C	
Mold Temperature	82.2 - 110	°C	
Back Pressure	0.172 - 0.344	MPa	
Screw Speed	30 - 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

