# megol® DP2154 60

## Styrene Ethylene Butylene Styrene Block Copolymer

API SpA

#### Message:

megol® DP2154 60 is a Styrene Ethylene Butylene Styrene Block Copolymer (SEBS) product. It can be processed by injection molding and is available in Europe. Characteristics include:

Characteristics includ Chemical Resistant Eco-Friendly/Green Fast Molding Cycle Good Processability Good UV Resistance

#### General Information

Features

Acid Resistant
Base Resistant
Detergent Resistant
Fast Molding Cycle
Good Chemical Resistance
Good Processability
Good UV Resistance
Good Weather Resistance
High Heat Resistance
Low Temperature Resistant
Ozone Resistant
Recyclable Material

Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.27	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	60		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
	4.50	MPa	
100% Strain	2.10	MPa	
300% Strain	3.90	MPa	
Tensile Elongation (Break)	400	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength <sup>1</sup>	30.0	kN/m	ASTM D624
Compression Set			ASTM D395
23°C, 72 hr	40	%	

70°C, 24 hr	70	%	
100°C, 24 hr	80	%	
NOTE			
1.	Without Notch		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

### Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

