

Sindustris PC GN1003FH

Polycarbonate

Sincerity Australia Pty Ltd.

Message:

Sindustris PC GN1003FH is a Polycarbonate (PC) material. It is available in Asia Pacific for injection molding.

Important attributes of Sindustris PC GN1003FH are:

Flame Rated

Flame Retardant

Chemical Resistant

Halogen Free

Heat Resistant

Typical applications include:

Electrical/Electronic Applications

Housings

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
	Good Chemical Resistance		
	Halogen Free		
	High Heat Resistance		
	High Impact Resistance		
Uses	Electrical/Electronic Applications		
	Housings		
UL File Number	E306922		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	13	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	61.8	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	100	%	ASTM D638
Flexural Modulus ³ (3.20 mm)	2450	MPa	ASTM D790
Flexural Strength ⁴ (3.20 mm)	96.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C, 3.20 mm	120	J/m	
23°C, 3.20 mm	740	J/m	
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.40 mm)	121	°C	ASTM D648
Vicat Softening Temperature	135	°C	ASTM D1525 ⁵
RTI Elec	80.0	°C	UL 746
RTI Imp	80.0	°C	UL 746
RTI Str	80.0	°C	UL 746
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.50 mm	V-0		
	V-0		
2.00 mm	5VB		

Injection	Nominal Value	Unit
Drying Temperature	90.0 to 100	°C
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.020	%
Rear Temperature	270 to 285	°C
Middle Temperature	275 to 290	°C
Front Temperature	275 to 290	°C
Nozzle Temperature	270 to 285	°C
Processing (Melt) Temp	275 to 285	°C
Mold Temperature	80.0 to 100	°C
Back Pressure	1.96	MPa
Screw Speed	40 to 80	rpm

NOTE		
1.	50 mm/min	
2.	50 mm/min	
3.	10 mm/min	
4.	10 mm/min	
5.	Rate A (50°C/h), Loading 2 (50 N)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT