

MAJ'ECO FT150BS - 1199

Biodegradable Polymers

AD majoris

Message:

MAJ'ECO FT150BS-1199 is a biopolymer compound intended for injection moulding.
MAJ'ECO FT150BS-1199 has been developed especially for demanding applications in various engineering sectors.

APPLICATIONS

Product such as:

- Boxes
- Racks
- Technical components

General Information			
Features	Updatable resources		
	Recyclable materials		
Uses	Bracket		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.17	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/5.0 kg)	27	g/10 min	ISO 1133
Molding Shrinkage (2.00 mm)	1.0	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2850	MPa	ISO 527-2/1
Tensile Stress (Break)	33.0	MPa	ISO 527-2/50
Flexural Modulus ¹	2400	MPa	ISO 178
Flexural Stress	61.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	50	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	105	°C	ISO 75-2/B
1.8 MPa, not annealed	81.0	°C	ISO 75-2/A
Flammability	Nominal Value	Test Method	
Flame Rating	HB	UL 94	
Injection	Nominal Value	Unit	
Processing (Melt) Temp	160 - 190	°C	
Mold Temperature	30.0 - 50.0	°C	
Injection Rate	Moderate		
Injection instructions			

Holding pressure: 50 to 70% of the injection pressure

NOTE

1. 2.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

