

Arnitel® EL740

Thermoplastic Copolyester Elastomer
DSM Engineering Plastics

Message:

Arnitel® EL740 is a Thermoplastic Copolyester Elastomer (TPC-ET) material. It is available in Asia Pacific, Europe, or North America for injection molding. Primary attribute of Arnitel® EL740: Flame Rated.

General Information			
UL YellowCard	E47960-240194		
Processing Method	Injection Molding		
Multi-Point Data	Shear Modulus vs. Temperature (ISO 11403-1)		
	Viscosity vs. Shear Rate (ISO 11403-2)		
Physical	Nominal Value	Unit	Test Method
Density	1.29	g/cm ³	ISO 1183
Apparent Density	0.83	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	18.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	2.0	%	
Flow	1.8	%	
Water Absorption			ISO 62
Saturation, 23°C	0.60	%	
Equilibrium, 23°C, 50% RH	0.15	%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 3 sec)	70		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	800	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Break	43.0	MPa	
5.0% Strain	30.0	MPa	
10% Strain	34.0	MPa	
50% Strain	25.0	MPa	
100% Strain	26.0	MPa	
Nominal Tensile Strain at Break	360	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	6.0	kJ/m ²	
23°C	10	kJ/m ²	
Notched Izod Impact Strength (23°C)	9.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method

Heat Deflection Temperature (0.45 MPa, Unannealed)	120	°C	ISO 75-2/B
Vicat Softening Temperature	160	°C	ISO 306/B50
Melting Temperature ¹	221	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow	1.7E-4	cm/cm/°C	
Transverse	1.7E-4	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	IEC 60093
Electric Strength	23	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	3.70		
1 MHz	3.30		
Dissipation Factor (1 MHz)	0.030		IEC 60250
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flammability Classification (1.60 mm)	HB		IEC 60695-11-10, -20
Injection	Nominal Value	Unit	
Drying Temperature	100	°C	
Drying Time	4.0 to 6.0	hr	
Rear Temperature	200 to 220	°C	
Middle Temperature	210 to 230	°C	
Front Temperature	220 to 240	°C	
Nozzle Temperature	230 to 250	°C	
Processing (Melt) Temp	230 to 250	°C	
Mold Temperature	20.0 to 50.0	°C	
Injection Rate	Moderate-Fast		
Back Pressure	3.00 to 10.0	MPa	
Screw Compression Ratio	2.5:1.0		
Extrusion	Nominal Value	Unit	
Melt Temperature	230 to 260	°C	
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

