

# SABIC® SUPEER™ 8315

Metallocene Linear Low Density Polyethylene

Saudi Basic Industries Corporation (SABIC)

Message:

SABIC® SUPEER™ 8315 is an ethylene-octene copolymer produced via Nexlene™ Technology. It performs well in a wide range of general purpose and high performance LLDPE cast film applications and has good impact strength and transparency.

Application

Typical applications for SABIC® SUPEER™ 8315 are stretch wrap film and silage film.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

General Information			
Features	Low density		
	Copolymer		
	Impact resistance, good		
	Octene comonomer		
Uses	Stretch winding		
	cast film		
	Agricultural application		
	General		
Appearance	Clear/transparent		
Processing Method	cast film		
Physical	Nominal Value	Unit	Test Method
Density	0.915	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	40	µm	
Tensile Strength			ASTM D882
MD: yield, 40 µm, extruded film	11.0	MPa	ASTM D882
TD: yield, 40 µm, extruded film	10.0	MPa	ASTM D882
MD: broken, 40 µm, extruded film	48.0	MPa	ASTM D882
TD: broken, 40 µm, extruded film	49.0	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: broken, 40 µm, extruded film	600	%	ASTM D882
TD: broken, 40 µm, extruded film	700	%	ASTM D882
Dart Drop Impact <sup>1</sup> (40 µm, cast film)	1000	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD: 40 µm, cast film	11	g	ASTM D1922
TD: 40 µm, cast film	25	g	ASTM D1922
Thermal	Nominal Value	Unit	Test Method

Melting Temperature	113	°C	Internal method
Optical	Nominal Value	Unit	Test Method
Haze (40.0 μm, cast film)	1.5	%	ASTM D1003
Additional Information	Nominal Value	Unit	
Cast Film Melt Temperature	250 - 300	°C	

Properties have been measured on cast film of 40μm

NOTE

1. F50

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

