## EVICOM™ GA6/266

# Flexible Polyvinyl Chloride INEOS Compounds

#### Message:

Specification: BS 2571:90 Types E4, E5, M4 and M5

Formulated without lead-based additives

General Information			
Features	Good Flexibility		
	Low (to None) Lead Content		
Uses	Profiles		
	Tubing		
Appearance	Opaque		
Forms	Pellets		
Processing Method	Extrusion		
	Profile Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.43	g/cm³	BS 2782 620A
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	65		BS 2782 365B
BS Softness	65		BS 2782 365A
Cold Bend	-40	°C	BS 2782 151A
Cold Flexibility	-34	°C	BS 2782 150B
Mechanical	Nominal Value	Unit	Test Method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

MPa

%

BS 2782 320A

BS 2782 320A

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

12.0

350

Tel: +86 21 5895 8519

Tensile Strength

Tensile Elongation (Break)

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

