

# Synthos EPS® 0308F/PL

Expanded Polystyrene

Synthos S.A.

## Message:

Synthos EPS® F /PL type 0308F, 0513F, 0816F and 1325F is self-extinguishing expandable polystyrene EPS with high content of pentane. The materials are formed by spherical polystyrene particles that contain a flame retardant system (content of HBCD < 0,5%) and a hydrocarbon blowing agent. Their surface is treated against gluing during processing and the formation of electrostatic charge. Due to the content of halogenated flame retardant and the residual blowing agent, the product is unsuitable for objects intended for direct contact with food.

Synthos EPS® 0308F/PL (Owipian FS 0308) is mainly used for production of shaped parts with high density and wall thickness less than 10 mm (e.g. shipping packaging for glass and electrical goods, building bricks, floor and roof shaped parts); production of smaller blocks with higher density or cutted profiles.

General Information			
Additive	Blowing Agent		
	Flame Retardant		
Features	Flame Retardant		
	Halogenated		
	Self Extinguishing		
Uses	Building Materials		
	Packaging		
	Profiles		
Appearance	White		
Forms	Spheres		
Physical	Nominal Value	Unit	Test Method
Apparent Density			Internal Method
-- <sup>1</sup>	< 0.02	g/cm <sup>3</sup>	
-- <sup>2</sup>	0.02 to 0.04	g/cm <sup>3</sup>	
Moisture Content	< 7000	ppm	Internal Method
Particle Size - >95% between	315 to 800	µm	Internal Method
Reaction to Fire			
--	B1		DIN 4102
--	Class E		EN 13501-1
Blowing Agent	< 7.0	wt%	Internal Method
NOTE			

1.	The laboratory tests of expanded beads bulk density are made according to Polish Standard PN-90/C-89298 using the following expansion times: 0308 and 0513: 12 min., 0816: 10 min., 1325: 6 min.
----	--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------

2.

The typical bulk density indicates values obtained during single-step pre-foaming on continuous pre-foaming devices. Lower values of bulk density can be achieved only after multiple pre-expansion.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

