THERMOLAST® K TC8TPZ (Series: GP/AP)

Thermoplastic Elastomer

KRAIBURG TPE

Good weathering resistance

Message:

The GP/AP Series is your material solution for technical applications with excellent adhesion to PP. The compounds are available in natural and black colors. Typical applications Function and design elements Handles (tools, toolboxes, skipoles) Soft touch for grips, switches and mats Material advantages Adhesion to PP Easy coloring (compounds in natural colors) Easy flowing Excellent mechanical properties

General Information				
Features	Good Adhesion			
	Good Flow			
	Good Weather Resistance			
Uses	Handles			
	Soft Touch Applications			
	Switches			
Appearance	Black			
Processing Method	Injection Molding			
Physical	Nominal Value	Unit	Test Method	
Density	1.10	g/cm³	ISO 1183	
Hardness	Nominal Value	Unit	Test Method	
Shore Hardness (Shore A)	79		ISO 7619	
Elastomers	Nominal Value	Unit	Test Method	
Tensile Stress ¹ (Yield)	9.00	MPa	ISO 37	
Tensile Elongation ² (Break)	650	%	ISO 37	
Tear Strength ³	29	kN/m	ISO 34-1	
Compression Set ⁴			ISO 815	
23°C, 72 hr	30	%		
70°C, 24 hr	50	%		
100°C, 24 hr	78	%		
Injection	Nominal Value	Unit		
Drying Temperature	60.0 to 80.0	°C		
Drying Time	2.0 to 4.0	hr		
Rear Temperature	180	°C		

Middle Temperature	200	°C
Front Temperature	220	°C
Mold Temperature	25.0 to 40.0	°C
Injection Pressure	20.0 to 100	MPa
Back Pressure	2.00 to 10.0	MPa
NOTE		
NOTE 1.	Type S2, 200 mm/min	
	Type S2, 200 mm/min Type S2, 200 mm/min	
1.		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

