

Arnitel® PB420-B

Thermoplastic Copolyester Elastomer
DSM Engineering Plastics

Message:

Arnitel® PB420-B is a Thermoplastic Copolyester Elastomer (TPC-ET) material. It is available in Asia Pacific, Europe, or North America for blow molding.

General Information			
Uses	Blow Molding Applications		
Processing Method	Blow Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.18	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (230°C/10.0 kg)	11.0	cm ³ /10min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D, 3 sec)	37		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	70.0	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Break	19.0	MPa	
5.0% Strain	3.50	MPa	
10% Strain	6.00	MPa	
50% Strain	11.6	MPa	
100% Strain	15.2	MPa	
Nominal Tensile Strain at Break	180	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	No Break		
23°C	No Break		
Notched Izod Impact Strength			ISO 180/1A
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	65.0	°C	ISO 75-2/B
Melting Temperature ¹	212	°C	ISO 11357-3
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

