

KOPLA PP KPZ1022

Polypropylene

KOPLA Co., Ltd.

Message:

KOPLA PP KPZ1022 is a Polypropylene material filled with glass\mineral. It is available in Asia Pacific.

Important attributes of KOPLA PP KPZ1022 are:

Flame Rated

Good Aesthetics

Warp Resistant

Typical applications include:

Automotive

Electrical/Electronic Applications

General Information			
Filler / Reinforcement	Glass\Mineral		
Features	Good Surface Finish		
	Low Warpage		
Uses	Automotive Exterior Trim		
	Electrical Parts		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.60 to 1.0	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	100		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	88.3	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	3.0	%	ASTM D638
Flexural Modulus (23°C)	5880	MPa	ASTM D790
Flexural Strength (23°C)	137	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	130	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	147	°C	
1.8 MPa, Unannealed	95.0	°C	
Melting Temperature	163	°C	
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT