

ALTECH® PA66 A 2015/710 GF15 IM

Polyamide 66
ALBIS PLASTIC GmbH

Message:

ALTECH® PA66 A 2015/710 GF15 IM is a Polyamide 66 (Nylon 66) product filled with 15% glass fiber. It is available in Asia Pacific, Europe, or North America.

Characteristics include:

REACH Compliant
RoHS Compliant
Heat Stabilizer
High Gloss
Impact Modified

General Information			
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Additive	Heat Stabilizer		
	Impact Modifier		
Features	Heat Stabilized		
	High Gloss		
	Impact Modified		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	1.16	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4100	MPa	ISO 527-2
Tensile Stress (Break)	80.0	MPa	ISO 527-2
Tensile Strain (Break)	4.3	%	ISO 527-2
Flexural Modulus	3550	MPa	ISO 178
Flexural Stress	120	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	22	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength	69	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	238	°C	ISO 75-2/A
Vicat Softening Temperature	228	°C	ISO 306/B50
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0 to 12	hr	
Suggested Max Moisture	0.15	%	

Processing (Melt) Temp	280 to 300	°C
Mold Temperature	80.0 to 90.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

