

Desmopan® DP 9395AU

Thermoplastic Polyurethane Elastomer (Polyether)

Covestro - PUR

Message:

Extrusion- and injection molding grade; with special UV stabilizers; very good hydrolysis and microbial resistance; good low-temperature flexibility; Application; Pneumatic hoses; Profiles; Cable sheathings; Injection molded engineering parts

General Information			
Additive	UV Stabilizer		
Features	Hydrolysis Resistant		
	Low Temperature Flexibility		
	Microbe Resistant		
Uses	Cable Jacketing		
	Engineering Parts		
	Hose		
	Hydraulic Applications		
	Profiles		
RoHS Compliance	RoHS Compliant		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1150	kg/m ³	ISO 1183 ¹
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868 ²
Shore A, 3 sec	95		
Shore D, 15 sec	46		
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress ³			DIN 53504
Break, 23°C	52.7	MPa	
10% Strain, 23°C	6.50	MPa	
50% Strain, 23°C	11.4	MPa	
100% Strain, 23°C	13.8	MPa	
300% Strain, 23°C	30.0	MPa	
Tensile Strain ⁴ (Break, 23°C)	440	%	DIN 53504
Abrasion Resistance (23°C)	30.0	mm ³	ISO 4649-A
Tensile Storage Modulus			ISO 6721-1,-4
-20°C	440	MPa	

20°C	104	MPa	
60°C	55.0	MPa	
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ⁵ (23°C)	100	kN/m	ISO 34-1
Compression Set			ISO 815
23°C, 72 hr	22	%	
70°C, 24 hr	40	%	
Injection	Nominal Value	Unit	
Processing (Melt) Temp	210 to 230	°C	
Mold Temperature	20.0 to 40.0	°C	
Extrusion	Nominal Value	Unit	
Melt Temperature	200 to 220	°C	
NOTE			

- | | |
|----|---|
| 1. | Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted. |
| 2. | Tested in accordance with ISO 10350. 23°C/50%r.h. unless otherwise noted. |
| 3. | 200 mm/min |
| 4. | 200 mm/min |
| 5. | 500 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

