

BESTNYL SI25VI01A

Polyamide 6

Triesa Plastics

Message:

Polyamide 6 natural lubrified with 25% glass fibre reinforcement

General Information			
Filler / Reinforcement	Glass Fiber,25% Filler by Weight		
Additive	Lubricant		
Features	Lubricated		
Appearance	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.30	g/cm ³	ISO 1183
Molding Shrinkage	0.30	%	ISO 294-4
Ash Content	25	%	Internal Method
Humidity - Pellets	0.20	%	ISO 1110
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	79		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8000	MPa	ISO 527-2
Tensile Stress	143	MPa	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	7.5	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	43	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	215	°C	ISO 75-2/B
1.8 MPa, Unannealed	200	°C	ISO 75-2/A
Vicat Softening Temperature	> 200	°C	ISO 306
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Electric Strength	40	kV/mm	IEC 60243-1
Flammability	Nominal Value	Unit	Test Method
Burning Rate	< 100	mm/min	FMVSS 302
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	100	°C	

Drying Time	2.0 to 4.0	hr
Processing (Melt) Temp	230 to 240	°C
Mold Temperature	70.0 to 80.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT