

LNP™ VERTON™ NV006E compound

Polycarbonate + ABS

SABIC Innovative Plastics

Message:

LNP VERTON NV006E is a compound based on PC/ABS resin containing Long Glass Fiber. Added features of this material include: Easy Molding.

Also known as: LNP* VERTON* Compound PCA-F-7006 EM

Product reorder name: NV006E

General Information			
Filler / Reinforcement	Long glass fiber		
Features	Good formability		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.39	g/cm ³	ASTM D792
--	1.35	g/cm ³	ISO 1183
Molding Shrinkage			
Flow: 24 hours	0.10	%	ASTM D955
Transverse flow: 24 hours	0.50	%	ASTM D955
Vertical flow direction: 24 hours	0.52	%	ISO 294-4
Flow direction: 24 hours	0.11	%	ISO 294-4
Water Absorption (24 hr, 50% RH)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	11000	MPa	ASTM D638
--	10000	MPa	ISO 527-2/1
Tensile Strength			
Yield	132	MPa	ASTM D638
Yield	150	MPa	ISO 527-2
Fracture	130	MPa	ASTM D638
Fracture	150	MPa	ISO 527-2
Tensile Elongation			
Yield	1.6	%	ASTM D638
Yield	2.0	%	ISO 527-2
Fracture	1.7	%	ASTM D638
Fracture	2.0	%	ISO 527-2
Flexural Modulus			
--	8270	MPa	ASTM D790
--	9000	MPa	ISO 178
Flexural Strength			
--	193	MPa	ASTM D790
--	123	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	260	J/m	ASTM D256
23°C ²	25	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ³ (23°C)	48	kJ/m ²	ISO 180/1U
Instrumented Dart Impact (23°C, Energy at Peak Load)	14.2	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	144	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	135	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ⁴	137	°C	ISO 75-2/Af
Linear thermal expansion coefficient			
Flow: -40 to 40°C	4.1E-5	cm/cm/°C	ASTM E831
Flow: -40 to 40°C	4.3E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 40°C	5.2E-5	cm/cm/°C	ASTM E831, ISO 11359-2
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

