

BIOLLOY KG340

Polylactic Acid + ABS
Techno Polymer Co, Ltd.

Message:

BIOLLOY KG340 is a Polylactic Acid + ABS (PLA+ABS) product. It is available in Asia Pacific or North America.

Characteristics include:

Eco-Friendly/Green

Rigid

General Information			
Features	General Purpose		
	High Rigidity		
	Renewable Resource Content		
Physical	Nominal Value	Unit	Test Method
Density	1.21	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	690	g/10 min	ISO 1133
Molding Shrinkage	0.60 to 0.80	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	117		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	68.0	MPa	ISO 527-2
Flexural Modulus	3270	MPa	ISO 178
Flexural Stress	95.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	6.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	56.0	°C	ISO 75-2/B
Injection	Nominal Value	Unit	
Drying Temperature	65.0	°C	
Rear Temperature	190 to 260	°C	
Middle Temperature	190 to 260	°C	
Front Temperature	190 to 260	°C	
Mold Temperature	40.0 to 80.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

