

AKROTEK® PEEK TM natural (5069)

Polyetheretherketone

AKRO-PLASTIC GmbH

Message:

AKROTEK® PEEK TM natural (5069) is an unreinforced polyetheretherketone with good tribological properties
Applications are mainly elements in the automotive-, aeronautical-, industrial- and medical engineering that require low friction and wear values in a temperature environment above 150°C

General Information			
Features	Good Wear Resistance		
	Low Friction		
Uses	Aerospace Applications		
	Automotive Applications		
	Industrial Applications		
	Medical/Healthcare Applications		
Appearance	Natural Color		
Resin ID (ISO 1043)	PEEK		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.40	g/cm³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3500	MPa	ISO 527-2/1
Tensile Stress (Yield)	75.0	MPa	ISO 527-2/50
Tensile Strain (Break)	> 20	%	ISO 527-2/50
Flexural Modulus ¹	3500	MPa	ISO 178
Flexural Stress ²	125	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.0	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	110	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
1.8 MPa, Unannealed	150	°C	ISO 75-2/A
8.0 MPa, Unannealed	140	°C	ISO 75-2/C
Melting Temperature ³	342	°C	DIN EN 11357-1
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	V-0		UL 94
NOTE			
1.	2.0 mm/min		
2.	2.0 mm/min		
3.	10 K/min, DSC		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

