

Arnite® A-X07302 (AV2 390 XT-P)

Polyethylene Terephthalate

DSM Engineering Plastics

Message:

Arnite® A-X07302 (AV2 390 XT-P) is a Polyethylene Terephthalate (PET) material filled with 50% glass fiber. It is available in Europe. Primary attribute of Arnite® A-X07302 (AV2 390 XT-P): Flame Rated.

General Information			
Filler / Reinforcement	Glass Fiber,50% Filler by Weight		
Features	Platable		
Physical	Nominal Value	Unit	Test Method
Density	1.78	g/cm³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow	0.80	%	
Flow	0.20	%	
Water Absorption			ISO 62
Saturation, 23°C	0.30	%	
Equilibrium, 23°C, 50% RH	0.12	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	19000	MPa	ISO 527-2
Tensile Stress (Break)	210	MPa	ISO 527-2
Tensile Strain (Break)	2.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	14	kJ/m²	
23°C	14	kJ/m²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	55	kJ/m²	
23°C	55	kJ/m²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	252	°C	ISO 75-2/B
1.8 MPa, Unannealed	240	°C	ISO 75-2/A
Melting Temperature ¹	255	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow	2.0E-5	cm/cm/°C	
Transverse	3.5E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+15	ohms · cm	IEC 60093
Relative Permittivity			IEC 60250

100 Hz	3.80		
1 MHz	3.50		
Dissipation Factor			IEC 60250
100 Hz	2.0E-3		
1 MHz	0.011		
Comparative Tracking Index	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flammability Classification			IEC 60695-11-10, -20
0.810 mm	HB		
1.47 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	100 to 120	°C	
Drying Time	3.0 to 12	hr	
Rear Temperature	270 to 280	°C	
Middle Temperature	270 to 290	°C	
Front Temperature	270 to 290	°C	
Nozzle Temperature	270 to 290	°C	
Processing (Melt) Temp	270 to 290	°C	
Mold Temperature	130 to 140	°C	
Injection Rate	Moderate-Fast		
Back Pressure	3.00 to 10.0	MPa	
Screw Compression Ratio	2.5:1.0		
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

