

Latimass 37 B01-01 D025

Polylactic Acid

LATI S.p.A.

Message:

Specific density compound based on Bio-Polymer (PLA, PHB, ...).

Special filler.

General Information			
Filler / Reinforcement	Filler		
Features	Renewable Resource Content		
Physical	Nominal Value	Unit	Test Method
Density	2.47	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 294-4
Across Flow : 2.00 mm	0.20 to 0.60	%	
Flow : 2.00 mm	0.20 to 0.60	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	8100	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	40.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	0.50	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	1.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	5.0	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	55.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	50.0	°C	ISO 75-2/A
Vicat Softening Temperature	60.0	°C	ISO 306/B50
Injection	Nominal Value	Unit	
Drying Temperature	40.0 to 50.0	°C	
Drying Time	6.0	hr	
Processing (Melt) Temp	180 to 200	°C	
Mold Temperature	15.0 to 30.0	°C	
Injection Rate	Moderate		
NOTE			
1.	60 MPa		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

