

# Manner Flexible PVC P1165

Flexible Polyvinyl Chloride

Manner Plastics, L.P.

## Message:

90°C Cold Resistant Extrusion Profile Compound. Designed to be used for SES C-3007 cold resistance tubing specification. This product complies with the European Union Restriction on Hazardous Substances (RoHS) directive.

General Information			
Uses	Tubing		
RoHS Compliance	RoHS Compliant		
Processing Method	Profile Extrusion		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.28 to 1.32	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 15 sec)	66		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	12.1	MPa	ASTM D638
Tensile Elongation (Break)	450	%	ASTM D638
Injection	Nominal Value	Unit	
Processing (Melt) Temp	171	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

