

LIHAN® A102

Polyamide 66

Nanjing Lihan Chemical Co., Ltd.

Message:

LIHAN® A102 is a Polyamide 66 (Nylon 66) product. It can be processed by injection molding and is available in Asia Pacific. Primary characteristic: flame rated.

General Information				
Forms		Pellets		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.13	--	g/cm ³	ISO 1183
Molding Shrinkage	1.0 to 1.4	--	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	1.0 to 1.4	--	%	ISO 62
Water Content	8.0 to 9.0	--	%	ISO 62
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness (R-Scale)	120	104		ISO 2039-2
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Stress (Break)	80.0	60.0	MPa	ISO 527-2
Tensile Strain (Break)	30	50	%	ISO 527-2
Flexural Modulus	2700	1200	MPa	ISO 178
Flexural Stress	100	45.0	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact Strength	3.8	10	kJ/m ²	ISO 180
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	210	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	65.0	--	°C	ISO 75-2/A
Melting Temperature	260	--	°C	DSC
CLTE - Flow	7.0E-5 to 1.0E-4	--	cm/cm/°C	ASTM D696
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+13	1.0E+10	ohms	ASTM D257
Dielectric Strength	20	--	kV/mm	ASTM D149
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (1.59 mm)	V-2	--		UL 94
Injection	Dry	Unit		
Processing (Melt) Temp	260 to 290		°C	
Mold Temperature	40.0 to 70.0		°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

