

Sumikon® AM-3500

Diallyl Phthalate

SBHPP

Message:

SUMIKON® AM-113 type J black-B is a short glass fiber reinforced, flame retardant, diallyl phthalate molding compound.

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
	Inorganic filler		
Features	Flame retardancy		
Appearance	Black		
Processing Method	Resin transfer molding		
	Compression molding		
	Injection molding		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.85	g/cm ³	JIS K6911
Molding Shrinkage - Flow	0.44	%	JIS K6911
Water absorption rate-by boiling	0.13	%	JIS K6911

Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	14000	MPa	JIS K6911
Flexural Strength	160	MPa	JIS K6911

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	3.6	kJ/m ²	JIS K6911

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	295	°C	JIS K6911

Electrical	Nominal Value	Unit	Test Method
Dielectric Strength ¹	12	kV/mm	JIS K6911
Comparative Tracking Index	600	V	IEC 60112
Insulation Resistance			JIS K6911
	-- ²	5.0E+14	ohms
	-- ³	1.0E+14	ohms

Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.200 mm)	V-0		UL 94

NOTE			
1.	Method B (step by step)		
2.	As molded		
3.	After boiling		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

