

SABIC® PPcompound 15T1040

Polypropylene Homopolymer
Saudi Basic Industries Corporation (SABIC)

Message:

SABIC® PPCOMPOUND 15T1040 is a general purpose, talc filled, heat stabilized homopolymer polypropylene compound, suitable for injection molding applications. The IMDS ID is 16487994

General Information			
Filler / Reinforcement	Talc		
Additive	Heat Stabilizer		
Features	General Purpose		
	Heat Stabilized		
	Homopolymer		
Uses	General Purpose		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.26	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.6	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	75		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	4240	MPa	ASTM D638
--	5530	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	33.0	MPa	ASTM D638
Yield	33.0	MPa	ISO 527-2/50
Break ³	28.0	MPa	ASTM D638
Break	31.5	MPa	ISO 527-2/1A/50
Tensile Elongation			
Yield ⁴	2.9	%	ASTM D638
Yield	2.1	%	ISO 527-2/50
Break ⁵	8.4	%	ASTM D638
Break	2.2	%	ISO 527-2/50
Flexural Modulus			
64.0 mm Span ⁶	5420	MPa	ISO 178
50.0 mm Span ⁷	3750	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA

-30°C ⁸	1.8	kJ/m ²	
23°C ⁹	2.0	kJ/m ²	
Notched Izod Impact			
23°C, 3.20 mm ¹⁰	11	J/m	ASTM D256
23°C ¹¹	1.9	kJ/m ²	ISO 180/1A
Unnotched Izod Impact ¹² (23°C, 3.20 mm)	230	J/m	ASTM D4812
Instrumented Dart Impact ¹³ (23°C, Energy at Peak Load)	1.10	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	137	°C	ASTM D648
0.45 MPa, Unannealed ¹⁴	137	°C	ISO 75-2/B
1.8 MPa, Unannealed, 3.20 mm	82.0	°C	ASTM D648
1.8 MPa, Unannealed ¹⁵	88.0	°C	ISO 75-2/A
Vicat Softening Temperature	158	°C	ISO 306/A50
Coefficient of Linear Thermal Expansion			ISO 11359-2
Flow : -30 to 100°C	54.5	µm/Mk	
Transverse : -30 to 100°C	110	µm/Mk	
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 100	°C	
Drying Time	2.0 to 4.0	hr	
Rear Temperature	190 to 230	°C	
Middle Temperature	200 to 250	°C	
Front Temperature	210 to 270	°C	
Nozzle Temperature	210 to 270	°C	
Processing (Melt) Temp	210 to 270	°C	
Mold Temperature	15.0 to 60.0	°C	
Back Pressure	1.00 to 1.50	MPa	
NOTE			
1.	50 mm/min		
2.	Type I, 50 mm/min		
3.	Type I, 50 mm/min		
4.	Type I, 50 mm/min		
5.	Type I, 50 mm/min		
6.	2.0 mm/min		
7.	1.3 mm/min		
8.	80*10*4mm, Cut		
9.	80*10*4 mm, Cut		
10.	63.5*12.7*3.2mm, Cut		
11.	80*10*4mm, Cut		
12.	63.5*12.7*3.2mm, Cut		
13.	2.20 m/sec		

14.	80*10*4mm, Cut
15.	80*10*4mm, Cut

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

