

Fasal® BIO 337

Biodegradable Polymers

Fasal Wood KG

Message:

Fasal BIO 337 a wood based material for injection moulding applications.

General Information			
Filler / Reinforcement	Wood fiber		
Features	Updatable resources		
	Biodegradable		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.16	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3900	MPa	ISO 527-2
Tensile Stress (Break)	32.9	MPa	ISO 527-2
Tensile Strain (Break)	1.9	%	ISO 527-2
Flexural Modulus	3500	MPa	ISO 178
Flexural Stress	56.6	MPa	ISO 178
Flexural Strain	3.1	%	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength	9.6	kJ/m ²	ISO 179/1fU
Injection	Nominal Value	Unit	
Drying Temperature	130	°C	
Drying Time	4.0	hr	
Rear Temperature	170	°C	
Middle Temperature	180	°C	
Front Temperature	180	°C	
Nozzle Temperature	190	°C	
Mold Temperature	20.0 - 60.0	°C	
Injection instructions			

Screw speed: 30 - 50% of maximumDynamic pressure: 20% of maximumInjection pressure: approx. 30 % higherthan with plastics

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

