

Absolac® 30GF20%

Acrylonitrile Butadiene Styrene
Styrolution

Message:

Absolac 30GF 20 is a glass filled grade

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight		
Uses	Pulley		
	Knob		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	10	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield, 23°C)	650	MPa	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact ¹ (23°C, 6.35 mm)	6.00		
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	105	°C	ASTM D1525 ²
Optical	Nominal Value		Test Method
Gardner Gloss (60°)	98		ASTM D523
NOTE			
1.	0.01 in Notch Radius		
2.	标准 B (120°C/h), 载荷2 (50N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT