

CoolPoly® D1202

Polypropylene
Celanese Corporation

Message:

CoolPoly D series of thermally conductive plastics transfers heat, a characteristic previously unavailable in injection molding grade polymers. CoolPoly is lightweight, netshape moldable and allows design freedom in applications previously restricted to metals. The D series is electrically non-conductive and can be used for its dielectric properties.

General Information			
Features	Heat conduction		
	Insulation		
	Good formability		
RoHS Compliance	RoHS compliance		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.39	g/cm ³	ISO 1183
Molding Shrinkage			ASTM D955
Flow	0.30	%	ASTM D955
Transverse flow	0.60	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.030	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5300	MPa	ISO 527-2
Tensile Stress (Yield)	24.0	MPa	ISO 527-2
Nominal Tensile Strain at Break	0.57	%	ISO 527-2
Flexural Modulus	6200	MPa	ISO 178
Flexural Stress	43.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	1.5	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength	6.8	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Specific Heat	1300	J/kg/°C	ASTM C351
Thermal Conductivity	5.0	W/m/K	ASTM C177
Additional Information			
The value listed as Thermal Conductivity, ASTM C177, was tested in accordance with ASTM E1461.The value listed as Mold Shrinkage, ASTM D955, was tested in accordance with ASTM D551.The value listed as Specific Heat ASTM C351, was tested in accordance with ASTM E1461Thermal Diffusivity, ASTM E1461: 0.025 cm ² /sec			
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	1.0 - 2.0	hr	

Dew Point	-20.0	°C
Rear Temperature	190 - 220	°C
Middle Temperature	210 - 230	°C
Front Temperature	215 - 245	°C
Processing (Melt) Temp	215 - 245	°C
Mold Temperature	20.0 - 65.0	°C
Injection Pressure	35.0 - 105	MPa
Injection Rate	Moderate-Fast	
Holding Pressure	20.0 - 55.0	MPa
Back Pressure	0.00 - 0.350	MPa
Screw Speed	20 - 60	rpm
Screw Compression Ratio	2.0:1.0	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

