

Next Nylon 6 Industrial Series NGF30-02BK

Polyamide 6

Next Polymers Ltd.

Message:

Description

PA6 Glass Fiber Reinforced FR Black compound

Product Applications

Industrial controls and Electrical insulation system

Benefits

This Red Phosphorous Flame retardent grade provides robust UL-94 VO, While offering good mechanical properties.

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 30% filler by weight		
Features		Insulation		
		Flame retardancy		
Uses		Industrial application		
Agency Ratings		EC 1907/2006 (REACH)		
RoHS Compliance		RoHS compliance		
Appearance		Black		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.42	--	g/cm ³	ASTM D792
Molding Shrinkage				ASTM D955
Flow	0.52	--	%	ASTM D955
Transverse flow	1.0	--	%	ASTM D955
Water Absorption				ASTM D570
23°C, 24 hr	1.7	--	%	ASTM D570
Saturation ¹	6.5	--	%	ASTM D570
Hardness	Dry	Conditioned	Unit	Test Method
Rockwell Hardness				ASTM D785
Class m	95	--		ASTM D785
Class r	120	--		ASTM D785
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength	120	90.0	MPa	ASTM D638
Tensile Elongation (Break)	4.0	6.0	%	ASTM D638
Flexural Modulus	7600	--	MPa	ASTM D790
Flexural Strength	210	180	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact (23°C)	78	98	J/m	ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method

Deflection Temperature Under Load				ASTM D648
0.45 MPa, not annealed	210	--	°C	ASTM D648
1.8 MPa, not annealed	180	--	°C	ASTM D648
Melting Temperature	220	--	°C	ASTM D2117
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+16	ohms	IEC 60093
Volume Resistivity	1.0E+16	1.0E+15	ohms·cm	IEC 60093
Dielectric Strength	26	24	kV/mm	IEC 60243-1
Comparative Tracking Index	> 450	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating (0.800 mm)	V-0	--		UL 94
Additional Information				

干燥

Possible formation of phosphates in humid warm environments.

Injection	Dry	Unit	
Drying Temperature - Hot Air Dryer	80.0	°C	
Drying Time	4.0 - 6.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	240 - 250	°C	
Middle Temperature	250 - 260	°C	
Front Temperature	260 - 270	°C	
Mold Temperature	65.0 - 85.0	°C	

NOTE

1. Immersed

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT