

Pyramid™ PEKK Plus® 07-P0684-01

Polyetherketoneketone

Polymics, Ltd.

Message:

Polyetherketoneketone, 35% glass filled, white

General Information			
Filler / Reinforcement	Glass Fiber,35% Filler by Weight		
Appearance	White		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.52	g/cm³	ASTM D792
Molding Shrinkage - Flow	0.30	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.040	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	103		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	13100	MPa	ASTM D638
Tensile Strength	193	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	11700	MPa	ASTM D790
Flexural Strength	262	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.318 mm)	8.0	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	321	°C	ASTM D648
Glass Transition Temperature	163	°C	ASTM E1356
Melting Temperature	360	°C	DSC
CLTE - Flow	1.6E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	5.1	ohms	ASTM D257
Volume Resistivity	2.5	ohms·cm	ASTM D257
Dielectric Strength	240	kV/mm	ASTM D149
Dielectric Constant	3.30		ASTM D150
Dissipation Factor	4.0E-3		ASTM D150

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

