

Verolloy DR210

Polycarbonate + SMA

PlastxWorld Inc.

Message:

Verolloy DR210 is a Polycarbonate + SMA (PC+SMA) product. It is available in Europe or North America.

Characteristics include:

Flame Rated

Flame Retardant

General Information			
UL YellowCard	E315545-100091186		
Features	Flame Retardant		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	51.0	MPa	ASTM D638
Tensile Elongation (Break)	80	%	ASTM D638
Flexural Modulus	2340	MPa	ASTM D790
Flexural Strength	82.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	480	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 6.35 mm)	95.0	°C	ASTM D648
Flammability	Nominal Value	Test Method	
Flame Rating			UL 94
1.50 mm, ALL	V-0		
2.50 mm, ALL	5V		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT