

EnCom ACCUTUF 3119 HS

Polypropylene

EnCom, Inc.

Message:

COPOLYMER POLYPROPYLENE

General Information			
Features	Copolymer		
Uses	Automotive Applications		
	Business Equipment		
	Lawn and Garden Equipment		
Appearance	Black		
	Colors Available		
	Natural Color		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.898	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.2	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	70		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	24.1	MPa	ASTM D638
Tensile Elongation (Break)	100	%	ASTM D638
Flexural Modulus	1220	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	160	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed)	93.3	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	93.3	°C	
Drying Time	2.0 to 4.0	hr	
Suggested Max Moisture	2.0E-3	%	
Rear Temperature	188 to 216	°C	
Middle Temperature	199 to 232	°C	

Front Temperature	199 to 232	°C
Nozzle Temperature	193 to 227	°C
Processing (Melt) Temp	204 to 260	°C
Mold Temperature	18.3 to 54.4	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

