

Chemlon® 240 G

Polyamide 6

Teknor Apex Company (Chem Polymer)

Message:

Chemlon® 240 G is a Polyamide 6 (Nylon 6) material filled with 40% glass fiber. It is available in Asia Pacific, Europe, or North America for injection molding. Primary attribute of Chemlon® 240 G: Flame Rated.

General Information			
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.46	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.15 to 0.35	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	183	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	2.5	%	
Break	2.5	%	
Flexural Modulus	9650	MPa	ASTM D790
Flexural Strength	262	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	150	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	207	°C	ASTM D648
Melting Temperature	216	°C	DSC
CLTE - Flow	5.3E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+18	ohms · cm	ASTM D257
Dielectric Strength (3.00 mm)	11	kV/mm	ASTM D149
Comparative Tracking Index (CTI)	500	V	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.810 mm)	HB		UL 94
Oxygen Index	22	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Suggested Max Moisture	0.20	%	
Suggested Max Regrind	25	%	
Rear Temperature	218 to 235	°C	
Middle Temperature	252 to 257	°C	

Front Temperature	252 to 271	°C
Nozzle Temperature	252 to 271	°C
Processing (Melt) Temp	249 to 271	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

