Tectron E1199

Thermoplastic Vulcanizate TECTRON Systems Pte Ltd

Message:

Thermoplastic vulcanizate with excellent oil, chemical and heat resistance. It can withstand temperatures ranging from 50°C to 130°C. Tectron E series are available in concentrate and compound with hardness ranging from 45A - 90A. The concentrate is designed for compounders to obtain olefenic TPVs with the addition of PP and other chemicals. It can also be used as an additive to improve the overall properties of your olefinic compounds.

General Information			
Features	Good chemical resistance		
	Heat resistance, high		
	Oil resistance		
Appearance	Yellow		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.900	g/cm³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (A-Scale)	80		ASTM D785
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	3.20	МРа	ASTM D412
Tensile Strength (Yield)	5.40	МРа	ASTM D412
Tensile Elongation (Break)	980	%	ASTM D412
Compression Set			ASTM D395
25°C, 22 hr	35	%	ASTM D395
100°C, 22 hr	70	%	ASTM D395
Injection	Nominal Value	Unit	
Drying Temperature	70.0	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	160 - 170	°C	
Middle Temperature	180 - 190	°C	
Front Temperature	180 - 200	°C	
Nozzle Temperature	190 - 210	°C	
Mold Temperature	30.0 - 40.0	°C	
Back Pressure	0.00 - 0.0800	MPa	
Screw Speed	50 - 110	rpm	
Injection instructions			

 $Injection\ Speed:\ 20\ to\ 80\ mm/s1st\ Stage-\ Boost\ Pressure:\ 1350\ to\ 6000 Hold\ Time\ (thick\ part):\ 2\ to\ 15\ sec$

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



Page 2