

QR Resin QR-1220

Polycarbonate + ABS

QTR, Inc.

Message:

Available with UV (V) or Release (R).

General Information			
Features	Good Impact Resistance		
	High Heat Resistance		
	Low Temperature Impact Resistance		
Appearance	Black		
	Colors Available		
	Natural Color		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.18 mm)	0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	55.2	MPa	ASTM D638
Flexural Modulus	2310	MPa	ASTM D790
Flexural Strength (Yield)	86.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	530	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	104	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	107	°C	
Drying Time	4.0 to 8.0	hr	
Drying Time, Maximum	8.0	hr	
Rear Temperature	246 to 282	°C	
Middle Temperature	249 to 293	°C	
Front Temperature	260 to 299	°C	
Nozzle Temperature	271 to 299	°C	
Processing (Melt) Temp	249 to 293	°C	
Mold Temperature	60.0 to 87.8	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

