

Elastoprene HS5060A NAT

Thermoplastic Elastomer

KMI Group, Inc.

Message:

Elastoprene HS5060A NAT is a 60 Shore A unfilled TPE for injection molding applications, offering good processibility, easy colorability, good heat resistance and FDA compliance.

Applications

Food containers, food closures, storage containers (gaskets/seals); utensils (grips), personal care (handles/grips), sporting goods (handles/grips)

General Information			
Features	Workability, good		
	Good coloring		
	Heat resistance, medium		
	Compliance of Food Exposure		
Uses	Handle		
	Washer		
	Personal care		
	Seals		
	Container		
	Soft handle		
	Food container		
	Sporting goods		
	Shell		
Agency Ratings	FDA not rated		
Appearance	Natural color		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.890	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	10	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw D, 10 seconds, extruded	58		ASTM D2240
Shore D, 10 seconds, injection molding	61		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	2.00	MPa	ASTM D412
Tensile Strength (Break)	8.17	MPa	ASTM D412
Tensile Elongation (Break)	630	%	ASTM D412
Tear Strength	28.0	kN/m	ASTM D624

Compression Set			ASTM D395B
23°C, 22 hr	20	%	ASTM D395B
70°C, 22 hr	53	%	ASTM D395B
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-60.0	°C	ASTM D746
Injection	Nominal Value	Unit	
Rear Temperature	171 - 199	°C	
Middle Temperature	177 - 210	°C	
Front Temperature	191 - 221	°C	
Nozzle Temperature	199 - 229	°C	
Processing (Melt) Temp	199 - 221	°C	
Mold Temperature	10 - 49	°C	
Injection Pressure	5.17 - 8.96	MPa	
Injection Rate	Fast		
Screw Speed	50 - 200	rpm	
Clamp Tonnage	2.8 - 4.8	kN/cm ²	
Cushion	5.08 - 12.7	mm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

