

Clariant Nylon 6/6 PA-113CF30

Polyamide 66
Clariant Corporation

Message:

Clariant Nylon 6/6 PA-113CF30 is a polyamide 66 (nylon 66) material, which contains a 30% carbon fiber reinforced material. This product is available in North America and is processed by injection molding.

The main features of Clariant Nylon 6/6 PA-113CF30 are:

- flame retardant/rated flame
- Flame Retardant
- Conductivity
- high strength
- Good processability

Typical application areas include:

- Wire and cable
- military applications
- business/office supplies
- Sporting goods
- medical/health care

General Information			
Filler / Reinforcement	Carbon fiber reinforced material, 30% filler by weight		
Additive	heat stabilizer		
Features	Conductivity		
	Rigidity, high		
	High strength		
	Workability, good		
	Good corrosion resistance		
	Good coloring		
	Good chemical resistance		
	Thermal Stability		
	Good toughness		
	Low or no water absorption		
Uses	Flame retardancy		
	Metal substitution		
	Military application		
	Business equipment		
	Sporting goods		
	Medical/nursing supplies		
Agency Ratings	UL 94		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method

Specific Gravity	1.28	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.20	%	ASTM D955
Water Absorption (24 hr)	0.50	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
Class m	98		ASTM D785
Class r	122		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	221	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	20000	MPa	ASTM D790
Flexural Strength	352	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	85	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	260	°C	ASTM D648
1.8 MPa, not annealed	257	°C	ASTM D648
CLTE - Flow	2.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+3	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	2.0 - 4.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	266 - 293	°C	
Middle Temperature	266 - 293	°C	
Front Temperature	266 - 293	°C	
Processing (Melt) Temp	266 - 288	°C	
Melt Temperature (Aim)	274	°C	
Mold Temperature	65.6 - 93.3	°C	
Injection Rate	Fast		
Back Pressure	0.345 - 0.689	MPa	
Screw Speed	20 - 100	rpm	
Cushion	3.18 - 6.35	mm	
Injection instructions			

Injection Pressure: Use minimum pressure to achieve 95% fill during the boost inj. pressure phase.Hold Pressure: 30% to 75% of injection pressure.Mold Temp. Target: 180°F Screw Speed Target: 75 RPM

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT