

CP PRYME® Nylon 6 N100HSL

Polyamide 6
Chase Plastics Services Inc.

Message:

CP PRYME® Nylon 6 N100HSL is a Polyamide 6 (Nylon 6) product. It is available in North America.

Characteristics include:

Heat Stabilizer
Lubricated

General Information				
Additive		Heat Stabilizer Lubricant		
Features		Heat Stabilized Lubricated		
Appearance		Natural Color		
Forms		Pellets		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.14	1.14	g/cm ³	ASTM D792
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Strength (23°C)	80.7	45.5	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	50	150	%	ASTM D638
Flexural Modulus (23°C)	2760	889	MPa	ASTM D790
Flexural Strength (Yield, 23°C)	107	43.4	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact (23°C)	43 J/m	No Break		ASTM D256
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ASTM D648
0.45 MPa, Unannealed	182	182	°C	
1.8 MPa, Unannealed	71.1	71.1	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

