

SEETEC EVA VA900

Ethylene Vinyl Acetate Copolymer

Lotte Chemical Corporation

Message:

SEETEC VA900 resin is produced by ExxonMobil Chemical's autoclave process technology.
SEETEC VA900 resin, with 28% VA content, is an excellent raw material in the application of hot melt adhesives.

General Information			
Additive	Antioxidant		
Features	Antioxidant		
Uses	Adhesives		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	0.950	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	150	g/10 min	ASTM D1238
Vinyl Acetate Content	28.0	wt%	Internal Method
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	21		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	< 40.0	°C	ASTM D1525
Melting Temperature	67.0	°C	Internal Method

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT