

Hytrel® PC988 NC010

THERMOPLASTIC POLYESTER ELASTOMER

DuPont Performance Polymers

Message:

82 Shore D High Performance Polyester Elastomer Developed for the Healthcare Industry

General Information			
Additive	Impact Modifier		
	UV Stabilizer		
Features	Impact Modified		
Uses	Film		
	Profiles		
	Sheet		
Forms	Pellets		
Processing Method	Calendering		
	Casting		
	Coating		
	Extrusion		
	Film Extrusion		
	Injection Molding		
	Profile Extrusion		
Part Marking Code (ISO 11469)	>TPC-ET<		
	TPC-ET		
Resin ID (ISO 1043)	TPC-ET		
Physical	Nominal Value	Unit	Test Method
Density	1.28	g/cm ³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	82		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	50.0	MPa	ISO 527-2
Tensile Strain (Break)	> 300	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	15	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Melting Temperature ¹	221	°C	ISO 11357-3
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

