

LNP™ LUBRICOMP™ DL001 compound

Polycarbonate
SABIC Innovative Plastics

Message:

LNP* LUBRICOMP* DL001 is a compound based on Polycarbonate resin containing 5% PTFE. Added features of this material include: Wear Resistant.
Also known as: LNP* LUBRICOMP* Compound DL-4010
Product reorder name: DL001

General Information			
UL YellowCard	E121562-101282870		
Additive	PTFE Lubricant (5%)		
Features	Good Wear Resistance		
	Lubricated		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow : 24 hr	0.70 to 0.90	%	ASTM D955
Across Flow : 24 hr	0.90 to 1.1	%	ASTM D955
Across Flow : 24 hr	0.96	%	ISO 294-4
Flow : 24 hr	0.78	%	ISO 294-4
Water Absorption (24 hr, 50% RH)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2070	MPa	ASTM D638
--	2190	MPa	ISO 527-2/1
Tensile Strength			
Yield	56.5	MPa	ASTM D638
Yield	54.0	MPa	ISO 527-2
Break	51.7	MPa	ASTM D638
Break	53.0	MPa	ISO 527-2
Tensile Elongation			
Yield	6.2	%	ASTM D638
Yield	6.1	%	ISO 527-2
Break	77	%	ASTM D638
Break	170	%	ISO 527-2
Flexural Modulus			
--	2070	MPa	ASTM D790
--	2100	MPa	ISO 178
Flexural Stress	70.0	MPa	ISO 178

Coefficient of Friction			ASTM D3702 Modified
vs. Itself - Dynamic	0.39		
vs. Itself - Static	0.32		
Wear Factor - Washer	91.5	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	160	J/m	ASTM D256
23°C ²	13	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	2400	J/m	ASTM D4812
23°C ³	180	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	39.6	J	ASTM D3763
--	49.4	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	142	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ⁴	142	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	132	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁵	129	°C	ISO 75-2/Af
CLTE			ASTM E831, ISO 11359-2
Flow : -40 to 40°C	7.4E-5	cm/cm/°C	
Transverse : -40 to 40°C	7.6E-5	cm/cm/°C	
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	293 to 304	°C	
Middle Temperature	304 to 316	°C	
Front Temperature	310 to 321	°C	
Processing (Melt) Temp	299 to 316	°C	
Mold Temperature	82.2 to 110	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

