

Karina CLEAR PVC COMPOUND -E

80/215-IS-RG

Polyvinyl Chloride

Karina Ind. e Com. de Plásticos Ltda

Message:

NON TOXIC PVC COMPOUND RECOMMENDED FOR BLOW MOLDED BOTTLES FOR VEGETABLE OILS PACKAGING.

| General Information | | | |
|--------------------------------------|-------------------|-------------------|---------------|
| Features | Non-Toxic | | |
| Uses | Bottles | | |
| | Packaging | | |
| Appearance | Clear/Transparent | | |
| Processing Method | Blow Molding | | |
| Physical | Nominal Value | Unit | Test Method |
| Density ¹ | 1.32 to 1.36 | g/cm ³ | IEC 60811-1-3 |
| Color | OK | | ME 12 |
| Clearness | 0.00OK | | ME 03 |
| Hardness | Nominal Value | Unit | Test Method |
| Durometer Hardness (Shore D, 15 sec) | 78 to 82 | | ASTM D2240 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Stress | > 34.3 | MPa | IEC 60811-1-1 |
| NOTE | | | |
| 1. | 24 hr | | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT