

ETILINAS PC4020

Medium Density Polyethylene
POLYETHYLENE MALAYSIA SDN BHD

Message:

ETILINAS PC4020 is designed specifically for coating/cladding of metal pipes and tubes.
ETILINAS PC4020 is based on a special medium density copolymer with exceptionally high resistance to environmental stress cracking and contains suitable additives necessary for ease of coating manufacture and to ensure long term weathering resistance.

General Information			
Additive	Carbon black (2%)		
Features	High ESCR (Stress Cracking Resistance)		
	Copolymer		
	Good weather resistance		
Uses	Pipeline coating		
Appearance	Black		
Forms	Particle		
Processing Method	Coating		
Physical	Nominal Value	Unit	Test Method
Density	0.947	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.30	g/10 min	ISO 1133
Environmental Stress-Cracking Resistance (F0)	1000	hr	ASTM D1693B
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 1 sec)	60		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	19.0	MPa	ISO 527-2/2
Tensile Strain (Break)	600	%	ISO 527-2/2
Flexural Modulus	750	MPa	ISO 178
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-100	°C	ASTM D746
Vicat Softening Temperature	116	°C	ISO 306/A
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Dielectric Strength	25	kV/mm	ASTM D149
Additional Information			
Density of Compound, ISO 1872/1, Annealed: 949 kg/m ³ Carbon Black Content, ISO 6964: 2.25%Thermal Conductivity, BS 874, 23°C: 0.4 W/m/°COxidation Induction Time, ISO TR10837, 210°C: >20 min			
Extrusion	Nominal Value	Unit	
Melt Temperature	200 - 225	°C	
Extrusion instructions			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

