AGC F-CLEAN®

Ethylene Tetrafluoroethylene Copolymer Asahi Glass Co., Ltd.

Message:

AGC F-CLEAN® is an Ethylene Tetrafluoroethylene Copolymer (ETFE) product. It is available in North America. Primary characteristic: chemical resistant.

General Information			
Features	Good Chemical Resistance		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.75	g/cm³	ASTM D792
Water Absorption (24 hr)	0.030	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	> 39.0	МРа	Internal Method
Tensile Elongation (Break)	200 to 510	%	Internal Method
Thermal	Nominal Value	Unit	Test Method
Continuous Use Temperature	150 to 180	°C	ASTM D794
Melting Temperature	260	°C	DSC
CLTE - Flow	9.4E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+17	ohms·cm	ASTM D257
Dielectric Strength	12	kV/mm	ASTM D149
Dielectric Constant (23°C, 1 MHz)	2.60		ASTM D150
Dissipation Factor			ASTM D150
60 Hz	6.0E-4		
1 kHz	8.0E-4		
1 MHz	5.0E-3		
1.00 GHz	0.010		
Arc Resistance	120	sec	ASTM D495

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

