

ALTECH® PP-H A 2030/652 GF30 UV CP

Polypropylene Homopolymer

ALBIS PLASTIC GmbH

Message:

ALTECH® PP-H A 2030/652 GF30 UV CP is a Polypropylene Homopolymer (PP Homopolymer) product filled with 30% glass fiber. It is available in Asia Pacific, Europe, or North America.

Characteristics include:

REACH Compliant

RoHS Compliant

Chemically Coupled

Homopolymer

UV Stabilized

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	UV Stabilizer		
Features	Chemically Coupled		
	Homopolymer		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	1.12	g/cm³	ISO 1183
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	3.00	cm³/10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6000	MPa	ISO 527-2
Tensile Stress (Break)	75.0	MPa	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Flexural Stress	115	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	10	kJ/m²	ISO 179/1eA
Charpy Unnotched Impact Strength	45	kJ/m²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	140	°C	ISO 75-2/A
Vicat Softening Temperature	135	°C	ISO 306/B50
Injection	Nominal Value	Unit	Test Method
Drying Temperature	80.0 to 120	°C	
Drying Time	2.0 to 3.0	hr	
Processing (Melt) Temp	200 to 270	°C	
Mold Temperature	20.0 to 90.0	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

