

SNOLEN® IM 26/59

High Density Polyethylene
JSC Gazprom neftekhim Salavat

Message:

CHARACTERISTIC PROPERTIES
High hardness. Good flow characteristics. Low deformation.
MAJOR APPLICATIONS
Containers. Components for machine building. Lids.

General Information			
Features	Good Flow		
	High Density		
	High Hardness		
Uses	Containers		
	Lids		
	Machine/Mechanical Parts		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	0.955 to 0.959	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ISO 1133
190°C/2.16 kg	6.0 to 10	g/10 min	
190°C/5.0 kg	20 to 26	g/10 min	
Environmental Stress-Cracking Resistance ¹ (80°C, 2% Arkopal)	1.50	hr	ISO 16770
Melt Flow Ratio	2.30 to 3.30		
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	64		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - Secant (23°C)	1350	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield	29.0	MPa	
Break	30.0	MPa	
Tensile Strain			
Yield	10	%	ISO 527-2
Break	> 1000	%	ISO 527-2/50
Impact	Nominal Value	Unit	Test Method
Charpy Unnotched Impact Strength (23°C)	2.5	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method

Brittleness Temperature	< -80.0	°C	ASTM D746
Vicat Softening Temperature	72.0	°C	ISO 306/B50
Injection	Nominal Value	Unit	
Processing (Melt) Temp	200 to 280	°C	
NOTE			
1.	@ 2.5 MPa		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT